

SPECIFICATIONS MD2000

PART 1 – GENERAL

INCLUDES

- A. Composite floor joist system of steel joists with cast-in-place concrete slab.

1.2 RELATED SECTIONS

- A. Section 03300 Cast-In-Place Concrete.

1.3 REFERENCES

- A. ACI 301 - Specifications for Structural Concrete
- B. ACI 318 - Building Code Requirements for Structural Concrete
- C. AISC Specification for the Design of Cold-Formed Steel Structural Members
- D. ASTM A 1008 Standard Specification for Steel. Sheet, Cold-Rolled, Carbon, Structural, High-Strength Low-Alloy and High Strength Low-Alloy with Improved Formability.
- E. ASTM C 39 - Standard Test Method for Compressive Strength of Cylinders Concrete Specimens.
- F. AWS D1.1 Structural Welding Code Steel.

1.4 DESIGN REQUIREMENTS

- A. Design of Composite Floor Joist System:
 - 1. Flexural Design: Ultimate Strength Method and as described by manufacturer.
 - 2. Joist Top Chord Member: AISC Specification for the Design of Cold-Formed Steel Structural Members.
 - 3. Concrete Slab: ACI 318
- B. Design Joists to Resist Combined Weight of:
 - 1. Wet concrete (specified slab thickness)
 - 2. Welded wire fabric reinforcement
 - 3. Metal Deck
 - 4. Construction Load: *20 psf* maximum

1.5 SUBMITTALS

- A. Comply with Section 01330 Submittal Procedures.
- B. Product Data: Submit manufacturer's product data for composite floor joist system.
- C. Shop Drawings: Submit shop drawings indicating material lists; mark numbers; types, locations and spacing of joists and accessories; and special conditions requiring top or bottom bracing.
 - 1. Calculated dimensions on shop drawings shall be used.
 - 2. Scaling of drawings shall not be permitted.

1.6 QUALITY ASSURANCE

- A. Welding Materials and Methods of Fabrication: Manufacturer's standard shop practice.
- B. Welder's Qualifications: Certify that each welder is *AWS certified in accordance with AWS D1.1.*
 - 1. Joist Repairs and Modifications in Field: Performed by *AWS certified welders in accordance with AWS D1.1.*

1.7 DELIVERY, STORAGE AND HANDLING

- A. Delivery:

SPECIFICATIONS MD2000

1. Deliver joists to site banded in nested bundles and tagged with Identification Plate attached at one end, at joist shoe.
 2. Indicate on Joist Identification Plates:
 - a. Manufacturer
 - b. Country (Plant)
 - c. Project number
 - d. Joist mark
- B. Storage:
1. Store materials in accordance with manufacturer's instructions.
 2. Protect materials from corrosion, deformation, and other damage.
 3. Store joists upright on level surface, off ground.
 4. Do not stack joists.
- C. Handling:
1. Protect joists from damage during unloading, storage, handling, and installation.
 2. Hoist joists by crane in accordance with manufacturer's instructions.

PART 2 - PRODUCTS

2.1 SUPPLIER

- A. Swirnow Structures LLC, 2801 Sisson Street
Baltimore, Maryland 21211-2902
Phone (800) 338-8833 / (410) 338-1122
Fax (410) 338-1124
Website: www.swirnow.com.

2.2 COMPOSITE FLOOR JOIST SYSTEM

- A. Designation: Hambro[®] Composite Floor Joist System
- B. Joists, Metal Deck, and Standard Bearing Shoes: Furnished by Supplier
- C. Joists:
1. Joist Depth: as indicated on the drawings.
 2. Top chord member:
 - a. Act as a continuous shear connector
 - b. ASTM A 1008, Grade 50, cold rolled steel, 13 gauge minimum
 - c. *Fy: 50,000 psi* minimum
 3. Bottom Chord Member:
 - a. Hot-rolled or cold-rolled steel angles
 - b. *Fy: 55,000 psi* minimum
 4. Web Members:
 - a. Hot-rolled steel bars, *7/16 inch* diameter minimum, some continuous
 - b. Bent at top chord joist locations
 - c. *Fy: 44,000 psi* minimum
 5. Shop painting: Rust-inhibitive primer
- D. Metal Deck: Metal deck shall be 1½" (min 9/16") deep, 22 gauge (min 28ga), type B, uncoated, light zinc or galvanized metal form deck. Metal deck shall be fastened or welded to Hambro joist deck support angles every 18" (max 24") along S-shaped top chord.
- E. Standard Bearing Shoes
1. Angle Shape: Steel, *4 inches* by *1 3/4 inches* by *1/4 inch*, *4 3/4 inches* wide, unless otherwise indicated on the drawings
 2. Shop Painting: Rust-inhibitive primer
- F. Concrete:
1. Minimum Ultimate Compressive Strength, *f'c: 3,000 psi @ 28 days*
 2. Standard Weight: *145 pcf*

SPECIFICATIONS MD2000

- 3. Maximum Aggregate Size: *3/4 inch*
- 4. As specified in Section 03300, unless specified otherwise in this section.
- G. Concrete Reinforcement: welded wire fabric.
 - 1. Size: As indicated on the drawings.
 - 2. *Fy*; 60,000 psi minimum
 - 3. Flat Sheets. Do not use rolls.
 - 4. As specified in Section 03300 unless specified otherwise in this section.

2.3 FABRICATION

- A. Fabrication: Manufacturer's standard shop practice.
- B. Joist Top Chord: Fabricate joist top chord to allow for *1-1/2 inches* embedment into concrete slab.
- C. Joist Cambers: Camber is optional, but when provided, approximate camber will be as follows:

Joist Span (Range)	Prefabricated Camber
<i>15 ft. to 20ft.</i>	<i>1/2 in. to 3/4 in.</i>
<i>20 ft. to 25 ft.</i>	<i>3/4 in. to 7/8 in.</i>
<i>25 ft. to 30 ft.</i>	<i>7/8 in. to 1 1/16 in.</i>
<i>30ft. to 40 ft.</i>	<i>1 1/16 in. to 1 1/2 in.</i>

2.4 SOURCE QUALITY CONTROL

- A. Joists:
 - 1. Manufacturer's facility having continuous quality control program and subjected to plant inspections by approved independent agency.
 - 2. Inspection shall include checking:
 - a. Size
 - b. Span
 - c. Assembly
 - d. Welds

PART 3 - EXECUTION

3.1 EXAMINATION

- A. Examine areas to receive composite floor joist system.
- B. Notify Engineer of conditions that would adversely affect installation.
- C. Do not start installation until unsatisfactory conditions are corrected.

3.2 INSTALLATION

- A. Install composite floor joist system in accordance with the following:
 - 1. Hambro Installation Guide
 - 2. Field-Use Shop Drawings
 - 3. Amendments issued by Supplier
- B. Construction Loads
 - 1. Do not exceed load-carrying capacity of composite floor joist system with construction loads.
 - 2. Concentrated construction loads: Do not place loads (i.e. bundles of metal deck or mesh), exceeding the design load of the slab, on joist system, but rather on supporting walls or beam.
 - 3. Construction loads exceeding design load capacity must be fully supported, and shored to grade.

SPECIFICATIONS MD2000

- C. Erect joists level, plumb and to proper locations and elevations.
- D. Perform shimming as required with metal shim material, ensuring total shoe contact.
- E. Special Conditions requiring top and/or bottom bracing shall be indicated on the Field-Use Shop Drawings, prepared by the Supplier.
- F. End Anchorage: Anchor or embed joist shoes as indicated on the drawings.
- G. Joist Sweep: After installation, allowable joist sweep shall be *1 inch in 20 feet*.
- H. Construction Loads: Do not exceed load carrying capacity of composite floor joist system with construction loads.
- I. Minimum Joist Bearing:
 - 1. Steel Supports: *2 1/2 inches*
 - 2. Masonry and Concrete Supports: *3 1/2 inches*
 - 3. Bearing Capacity of Supporting Units: Comply with applied shoe end reaction, based on minimum supplied bearing areas as follows:
 - a. Bearing on structural steel: *11.8 square inches*
 - b. Other Bearing Conditions: *16.6 square inches*
- J. Damaged Joists:
 - 1. Do not install damaged joists.
 - 2. Repair or replace damaged joists before installation.
 - 3. Do not make field repairs to damaged joists without written approval from the Engineer of Record.
 - 4. Make repairs to damaged joists in accordance with suggested repair details from the Supplier.
 - 5. Receive written approval from Engineer of Record before repair.

3.3 CONCRETE PLACEMENT

- A. Concrete:
 - 1. In accordance with ACI 301
 - 2. As specified in Section 03300, unless specified otherwise in this Section.
- B. Welded Wire Fabric:
 - 1. Laps: In accordance with ACI 318
 - 2. As specified in Section 03300, unless specified otherwise in this section.
- C. Place concrete to slab thickness as indicated on the drawings. *Do not pour concrete in excess of the thickness indicated on the drawings.*
- D. Maintain minimum depth of concrete cover above joist top chord in accordance with manufacturer's instructions.
- E. *Construction Loads: Do not drop bucket loads of concrete in concentrated area over joists.*
- F. Vibrate concrete lightly but thoroughly. Ensure full encasement of the joist top chord in concrete.
- G. Construction Joints:
 - 1. Parallel to Joists:
 - a. Locate construction joints midway between joists.
 - b. Do not locate construction joints closer than *6 inches* from top chord.
 - 2. Perpendicular to joists:

3.4 PROTECTION

- A. Protect concrete as required to avoid damage.

IMPORTANT ACCOUSTICAL NOTE:

The International Building Code (IBC) SEC 1 206 requires a minimum Sound Transmission Class (STC) and Impact Insulation Class (IIC) rating of 50.

The Design Professional should evaluate the specific requirements for the project and determine how the ratings will be achieved.

SPECIFICATIONS MD2000

Laboratory tests were performed on a Hambro assembly consisting of a concrete slab, the Hambro joists, metal furring channels and a drywall ceiling. Hambro was able to achieve a Sound Transmission Class (STC) = 57, and an Impact Insulation Class (IIC) = 30. The IIC is a rating designed to measure the impact sound insulation provided by floor/ceiling construction.

Most bare structural floor systems do not achieve IBC's minimum IIC rating of 50. The IIC of any assembly is strongly dependent on the floor finishes and underlayment. Bare concrete or direct applied hard floor finishes do not provide adequate protection against the transfer of impact noise. It is recommended that a pliable, resilient, insulation underlayment, or other method, be included wherever hard floor finishes such as ceramic tile or hardwood are used.

A wide variety of systems are available to address this issue. The Design Professional should evaluate the requirements for the project and determine how the ratings will be achieved.